

# Usage

- GST target will be used as sputter target in NMPF AJA sputter tool
- The thin film deposition is done at room temperature. Deposition at higher temperature to be avoided to avoid thermal degradation
- After deposition, capping of thin film to be done by TiN/Alumin to avoid surface oxidation of GST films
- Protective gears like hand gloves, face mask and safety goggles to be used while handling the target
- When not in use it will be stored in evacuated desiccators