

❖ Recipe for PPR Etch ❖

Temperature (Degree C)	Chamber servo pressure(mTorr)	RF power (w)	Bias Power(w)	Gases(scc)		Process Time	Etch rate
				CF4	CHF3		
250	1.5	1200	80	100	10	Max 15 Minuets.	-
