

Recipe for SOI and glass wafer bonding

| Temperature | Voltage applied and time | Total bonding time |
|---------------------|--|--------------------|
| 390 degrees Celsius | 400 V for 2 mins 600 V for 2 mins 800 V for 5 mins | 1 hour |